

**Europäisches Patentamt** 

**European Patent Office** 

Office européen des brevets



(11) EP 0 987 166 A1

(12)

# **EUROPEAN PATENT APPLICATION**

(43) Date of publication: 22.03.2000 Bulletin 2000/12

(21) Application number: 99118288.2

(22) Date of filing: 15.09.1999

(51) Int. CI.<sup>7</sup>: **B62D 21/11**, B60G 7/00, B21D 39/02, B21D 53/88, C22C 38/00, C22C 38/42

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE
Designated Extension States:

AL LT LV MK RO SI

AL LI LV IVIK NO SI

(30) Priority: 16.09.1998 IT TO980785

(71) Applicant: M.A.C. S.p.A. 10044 Pianezza (Torino) (IT) (72) Inventor: Azzolini, Ezio 10090 Sangano (Torino) (IT)


(74) Representative:

Fioravanti, Corrado et al Jacobacci & Perani S.p.A. Corso Regio Parco 27 I-10152 Torino (IT)

#### (54) A structural element for a motor vehicle

(57) A structural element for a motor vehicle, in particular, a frame (10) for supporting an engine and suspension units, is described. Two pressed sheet-steel half-shells (11, 12) with concave cross-sections are fitted together with their concave sides facing one another

to define a closed cross-section and are fixed together along respective outwardly-projecting peripheral rims (13, 14). The half-shells are connected by seaming of their rims (13, 14).



Description

[0001] The present invention relates to a structural element for a motor vehicle and, in particular, to a frame for supporting an engine and suspension units, of the type comprising a pair of pressed sheet-steel half-shells with concave cross-sections fitted together along a given axis with their concave sides facing one another to define a closed cross-section and fixed together along respective peripheral rims projecting outwardly and perpendicular to the given axis.

[0002] At the moment, the two superimposed halfshells of structural elements of this type are arranged for automatic welding by continuous seam welding along the perimeters of the half-shells.

[0003] The joining of the half-shells by welding has a first disadvantage owing to the fact that the welding often has non-homogeneous portions which require localized re-welding which is not always accepted by the vehicle manufacturer.

[0004] Moreover, the welds comprise minute cracks which, in time, may lead to localized breakages due to the dynamic stresses to which the structural element is subjected, particularly if it is a frame for supporting the engine and suspension units. In addition, the minute cracks in turn represent critical regions for corrosion.

**[0005]** Finally, the welding process is difficult to control from a qualitative point of view without considerable investment in control equipment.

[0006] The object of the present invention is to provide a load-bearing structural element for a motor vehicle which can prevent the problems mentioned above and which can be produced by a method of manufacture which leads to a reduction in costs in comparison with conventional solutions which provide for welding of the half-shells.

[0007] This object is achieved, according to the present invention, by means of a structural element of the type identified in the introductory portion of the description, characterized in that the half-shells are connected by seaming of their rims.

[0008] Further characteristics and advantages of the present invention will become clear in the course of the detailed description of an embodiment thereof, given with reference to the appended drawings provided by way of non-limiting example, in which:

Figure 1 is a general perspective view of a frame according to the present invention for supporting the engine and suspension units of a motor vehicle, and

Figure 2 is a cross-section taken on the line II-II of Figure 1, on an enlarged scale.

[0009] With reference initially to Figure 1, a structural element according to the present invention is generally indicated 10; in this embodiment, the structural element

units of a motor vehicle.

[0010] As also shown in Figure 2, the frame 10 is formed by joining together a pair of pressed sheet-steel half-shells 11, 12 having concave cross-sections. The two half-shells 11, 12 are fitted together and juxtaposed along an axis defined herein as vertical, with their concave sides facing one another so as jointly to define a closed cross-section (Figure 2).

[0011] The two half-shells 11, 12 have respective peripheral rims 13, 14 which project outwardly and horizontally; the rims 13 of the upper half-shell 11 have a width approximately twice that of the rims 14 of the lower half-shell 12 so that they can be turned over in a U-shaped arrangement around and beneath the rims 14 by a seaming operation, starting from an initial undeformed condition, indicated 13', in which these rims are initially straight.

[0012] The upper half-shell 11 is made of a sheet steel having a thickness  $s_1$  which is less than the thickness  $s_2$  of the sheet constituting the lower half-shell 12. This facilitates the bending of the rim 13 to be turned over; moreover, as can be understood from an observation of Figure 2, this configuration prevents water from collecting in the vicinity of the coupling rims since the end 13a of the rim 13 acts as a dripper for any water deposited on the outside of the upper half-shell 11.

[0013] The sheets used to form the half-shells 11, 12 and, in particular, the upper half-shell 11, the edge of which is bent into a U-shape, are made of a special high-strength steel such as, for example, that marketed by the firm Sollac with the reference DP 600. The use of this steel enables the thicknesses of the sheets to be reduced.

35 [0014] A steel of this type has the following chemical composition (% by weight):

C ≤ 0.100 Mn ≤ 0.800

5

10

15

20

25

30

40 P from 0.060 to 0.090

S ≤ 0.008 Si ≤ 450

Cu from 0.250 to 0.550

Ni ≤ 0.350

Cr from 0.450 to 0.650

[0015] With regard to the dimensions of the rims of a structural element which, as in the embodiment illustrated, has the functions of a front frame for supporting an engine and suspension units, the rims 14 of the lower half-shell 12 preferably have a width of between about 7 and about 9 mm which enables the two half-shells to be joined together firmly and renders the element composed thereof easily able to withstand the dynamic stresses to which such frames are normally subjected.

[0016] The seaming of the half-shells is performed substantially continuously along their peripheries,

50

55

10

15

25

30

4

except for the points at which one of the two half-shells forms projecting portions such as, for example, those indicated 15, to constitute means for fixing to other parts and components of the motor vehicle.

[0017] Naturally, the principle of the invention remaining the same, the forms of embodiment and details of construction may be varied widely with respect to those described and illustrated purely by way of non-limiting example, without departing from the scope of the invention as defined in the appended claims.

#### Claims

- A structural element for a motor vehicle, in particular, a frame (10) for supporting an engine and suspension units, of the type comprising a pair of pressed sheet-steel half-shells (11, 12) with concave cross-sections fitted together along a given axis with their concave sides facing one another to define a closed cross-section and fixed together along respective peripheral rims (13, 14) projecting outwardly and perpendicular to the given axis, characterized in that the half-shells are connected by seaming of the rims (13, 14).
- A structural element according to Claim 1, characterized in that the rims (13) of a first (11) of the half-shells are turned over onto the rims (14) of the second (12) of the half-shells.
- A structural element according to Claim 1, of the type in which one, upper half-shell (11) is superimposed vertically on the other, lower half-shell (12), characterized in that the rims (13) of the upper halfshell (11) are turned over around and beneath the rims (14) of the lower half-shell (12).
- 4. A structural element according to Claim 1, characterized in that the first half-shell (11), the rims (13) of which are turned over, is made of sheet metal having a thickness (s1) less than the thickness (s2) of the sheet steel constituting the second half-shell (12).
- 5. A structural element according to Claim 1, characterized in that at least the first half-shell (11) is made of a steel which has the following chemical composition (% by weight):

C ≤ 0.100 Mn ≤ 0.800

P from 0.060 to 0.090

S ≤ 0.008 Si ≤ 450

Cu from 0.250 to 0.550


Ni ≤ 0.350


Cr from 0.450 to 0.650

- 6. A structural element according to Claim 4, characterized in that the sheet-steel constituting the first half-shell (11) has a thickness of about 1.5 mm and in that the sheet-steel constituting the second half-shell (12) has a thickness of about 2 mm.
- 7. A structural element according to Claim 1, characterized in that the rim (14) of the second half-shell (12) has a width of between about 7 and about 9 mm, measured in a direction perpendicular to that in which the rim (14) extends.
- 8. A structural element according to Claim 1, characterized in that the seaming is performed substantially continuously along the peripheries of the two half-shells (11, 12).

50

55







# **EUROPEAN SEARCH REPORT**

Application Number EP 99 11 8288

Category	Citation of document with in of relevant passa		Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)	
X	DE 39 27 987 A (BAYE AG) 28 February 199	ERISCHE MOTOREN WERKE L (1991-02-28)	1	B62D21/11 B60G7/00	
Y	* the whole document	*	2	B21D39/02	
Υ	DE 26 59 081 A (VOL) 6 July 1978 (1978-0) * the whole document	7-06)	1,2	B21D53/88 C22C38/00 C22C38/42	
Y	DE 31 09 565 A (DAIN 14 October 1982 (198 * the whole document	32-10-14)	1,2		
X	FR 1 292 680 A (DAII 28 September 1962 ( * the whole document	1962-09-28)	1		
Υ	DE 10 74 416 B (DAI 28 January 1960 (196 * the whole documen	50-01-28)	1,2		
Y	PATENT ABSTRACTS OF JAPAN vol. 014, no. 203 (M-0966), 25 April 1990 (1990-04-25) & JP 02 041724 A (NISSAN MOTOR CO LTD), 9 February 1990 (1990-02-09) * abstract; figures 2,3,5,7 *		1,2	TECHNICAL FIELDS SEARCHED (Int.CI.7) B62D B60G B21D C22C	
Y	PATENT ABSTRACTS OF vol. 008, no. 032 (1) 10 February 1984 (1) & JP 58 188712 A (N) KK;OTHERS: 01), 4 November 1983 (19) * abstract; figure	M-275), 984-02-10) ISSAN JIDOSHA 83-11-04)	1,2		
	The present search report has I	-/			
	Place of search	Date of completion of the search		Examiner	
	THE HAGUE	6 December 1999	Ts	itsilonis, L	
X:pa Y:pa do A:teo	CATEGORY OF CITED DOCUMENTS rticularly relevant if taken alone rticularly relevant if combined with anot cument of the same category chnological background n-written disclosure	L : document cited	ple underlying the locument, but published in the application of the for other reasons.	o invention dished on, or n s	

5

# **EUROPEAN SEARCH REPORT**

Application Number

EP 99 11 8288

Category	Citation of document with inc of relevant passa		Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	DE 195 35 870 A (BLZ LASERZENTRUM G) 6 February 1997 (199 * column 1, line 1 - 1,2,5,8 * * column 7, line 55 * column 5, line 61	77-02-06)	*	
Α	PATENT ABSTRACTS OF vol. 012, no. 031 (M 29 January 1988 (198 & JP 62 184976 A (NI 13 August 1987 (1987 * abstract *	M-663), 38-01-29) ISSAN MOTOR CO LTD),	1-3	
A	PATENT ABSTRACTS OF vol. 017, no. 100 (0 26 February 1993 (19 & JP 04 289122 A (No. 14 October 1992 (1994) * abstract *	C-1030), 993-02-26) KK CORP),	5	TECHNICAL FIELDS SEARCHED (Int.Ci.7)
A	DE 35 40 520 A (VOLE 5 June 1986 (1986-0			
A	PATENT ABSTRACTS OF vol. 006, no. 172 (17 September 1982 (17 & JP 57 084267 A (M. 26 May 1982 (1982-0 * abstract; figures	M-154), 982-09-07) AZDA MOTOR CORP), 5-26)		
			-	
	The present search report has	been drawn up for all claims		
	Place of search	Date of completion of the sear	ch	Examiner
	THE HAGUE	6 December 19	99   Ts	itsilonis, L
Y:po do A:te O:n	CATEGORY OF CITED DOCUMENTS articularly relevant if taken alone articularly relevant if combined with and ocument of the same category ichnological background on-written disclosure termediate document	E : earlier pate after the fill ther D : document L : document	rinciple underlying the ent document, but put ing date cited in the application cited for other reason f the same patent fam	on Sa

### EP 0 987 166 A1

#### ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 99 11 8288

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06-12-1999

DE 3109565 A 14-10-1982 NONE  FR 1292680 A 28-09-1962 CH 384375 A DE 1144123 B  DE 1074416 B NONE  JP 02041724 A 09-02-1990 NONE  JP 58188712 A 04-11-1983 NONE  DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-1990 DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-1980	DE 3927987	Λ.	<del></del>		
DE 3109565 A 14-10-1982 NONE  FR 1292680 A 28-09-1962 CH 384375 A DE 1144123 B  DE 1074416 B NONE  JP 02041724 A 09-02-1990 NONE  JP 58188712 A 04-11-1983 NONE  DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-1990 DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-1980		^	28-02-1991	NONE	
FR 1292680 A 28-09-1962 CH 384375 A DE 1144123 B  DE 1074416 B NONE  JP 02041724 A 09-02-1990 NONE  JP 58188712 A 04-11-1983 NONE  DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-1990  DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-1980	DE 2659081	Α	06-07-1978	BR 7708622 A	22-08-1978
DE 1144123 B  DE 1074416 B NONE  JP 02041724 A 09-02-1990 NONE  JP 58188712 A 04-11-1983 NONE  DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-1990  DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-1980	DE 3109565	 А	14-10-1982	NONE	
JP 02041724 A 09-02-1990 NONE  JP 58188712 A 04-11-1983 NONE  DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-1990  DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-1980	FR 1292680	Α	28-09-1962		
JP 58188712 A 04-11-1983 NONE  DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-199  DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-198	DE 1074416	В		NONE	
DE 19535870 A 06-02-1997 NONE  JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-199  DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-198	JP 02041724	Α	09-02-1990	NONE	
JP 62184976 A 13-08-1987 NONE  JP 04289122 A 14-10-1992 JP 2745823 B 28-04-199  DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-198	JP 58188712	Α	04-11-1983	NONE	
JP 04289122 A 14-10-1992 JP 2745823 B 28-04-1990 DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-1980	DE 19535870	Α	06-02-1997	NONE	
DE 3540520 A 05-06-1986 NONE  JP 57084267 A 26-05-1982 JP 1448704 C 11-07-198	JP 62184976	Α	13-08-1987	NONE	
JP 57084267 A 26-05-1982 JP 1448704 C 11-07-198	JP 04289122	Α	14-10-1992	JP 2745823 B	28-04-1998
	DE 3540520	Α	05-06-1986	NONE	
	JP 57084267	Α	26-05-1982		11-07-198 15-12-198

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

7

FORM P0459

THIS PAGE BLANK (USPTO)